


**Plastazote® LD34****Low Density Polyethylene Foam
Property Data Sheet**

Plastazote® is a closed cell, cross-linked polyethylene foam manufactured using Zotefoams unique production process. This data sheet characterises Plastazote foam LD34 which is available in sheet form and is fabricated by modern techniques and can be thermoformed into shapes.

Property	Test Procedure	Units	LD34
Nominal Density - Skin/Skin	BS ISO 7214 1998	kg/m ³	34
Cell Size – Typical Diameter	Internal	mm	0.37
Compression Stress-Strain	BS ISO 7214 1998		
10% compression		kPa	51
25% compression		kPa	69
40% compression		kPa	102
50% compression		kPa	137
Compression Set	BS ISO 7214 1998		
25% comp., 22hr, 23°C	25 mm cell-cell		
½ hr recovery		% set	10
24hr recovery		% set	3
50% comp., 22hr, 23°C			
½ hr recovery		% set	22.5
24hr recovery		% set	13.5
Tensile Strength	ISO 7214 1998	kPa	440
Tensile Elongation		%	155
Tear Strength	BS EN ISO 8067 1995	N/m	785
Shore Hardness OO Scale	ISO 868 1985		
10mm cell/cell thickness		OO	58
Recommended operating temperature range*	Internal	°C	+100 max -70 min
Water vapour transmission	ISO 1663 1999	µg/m ² /sec	47-52
Temperature = 38°C			
Relative humidity gradient = 0/88%			
Permeability		ng/Pa/s/m	0.20-0.25
25mm mean thickness			
Water Absorption	ISO 2896-A 2001		
1 Day		%vol	<0.1
7 Days		%vol	<1.5
14 Days		%vol	<2
28 Days		%vol	<3
Thermal Conductivity	ISO 8302 1991	W /m.K	0.0405
mean temp of 10°C			
Flammability			
Automotive	FMVSS.302 – Burn rate	<100mm/min.	Pass: 7 mm and thicker
Horizontal Burn Rate	ISO 7214 1998		
5mm thick		mm/sec	1.6
13mm thick		mm/sec	1.0

*** RECOMMENDED OPERATING TEMPERATURE RANGE**

The maximum operating temperature shown is defined as the temperature which will typically cause a linear shrinkage of 5% after a 24hr exposure period, using sample dimensions of 100mm x 100mm x 25mm. This figure is provided for general guidance only. The actual level of shrinkage the foam will undergo at any particular temperature is dependant on a number of system variables such as, sample dimensions, cell size, loading conditions and exposure period. Please refer to Technical Bulletin T2 for more detailed information.

HEALTH & SAFETY

A separate data sheet (T5) entitled "Health and Safety Information" should be consulted.

PRODUCT SPECIFICATION

This Property Data Sheet provides typical properties on representative samples of material. For a product specification please refer to data sheet T7.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

Zotefoams plc
675 Mitcham Road
Croydon
CR9 3AL
United Kingdom
Telephone: +44 (0) 20 8664 1600
Telefax: +44 (0) 20 8664 1616

Zotefoams Inc.
55 Precision Drive
Walton, Kentucky,
41094
USA
Telephone: +1 859 371 4046
Freephone: (800) 362-8358 (US Only)
Telefax: +1 859 371 4734

Your Distributor:

Bright Star Construction Materials LLC

*P.O. Box : 12862, Dubai
United Arab Emirates
Tel: +971 4 2672773
Fax: +971 4 2671731
E-mail : bstar@emirates.net.ae
Website : www.brightstarllc.com*

Appointed by Zotefoams as "SPECIALIST CONVERTER"

PLASTAZOTE[®], EVAZOTE[®], SUPAZOTE[®] and PROPOZOTE[®] are registered trade marks of Zotefoams plc.

November 2006